

ECOSTICK® 1817

Description/Nature of the product

Acqueous dispersion of a polymer based on polyurethane modified, ca.50%

Application by

Spray gun, roller machine

Characteristics

Ideal to couple and fold leather, fabrics, linings, regenerated cardboards and greasy leather. Ideal for gluing PVC, nylon and ready made rubbers.

Instructions for use

Apply the adhesive on both sides. Let it dry, couple both sides within 10 minutes after the adhesive is dried and press. If the open time is exceeded, reactivate at 60°C, couple and press.

Open Time

Used as cold adhesive, the open time is 5 - 10 minutes depending on the quantity and the material on which it is applied. With the addition of hardener it can have a pot life of 4 hours and a useful time of 2 hours for the reactivation. Using the adhesive without hardener and with heat reactivation, from the time the adhesive film becomes dry, it has a useful time for the reactivation of up to 15 days. Storage conditions must be in the absence of dust and / or dirt and other types of contamination.

Remarks

When highest heat resistance is requested, we suggest adding Hardener.



Intercom Srl ® - P.iva e C.F. 06183210480

Address: Via della Gora, 13 - 50025 Montespertoli - Firenze - Italia

Phone: +39 0571 671096 - **Fax:** +39 0571 671151 - **Email:** info@intercomsas.it - **Web:** www.intercomsas.it